

PATENT ABSTRACTS OF JAPAN

(11)Publication number : **11-302338**

(43)Date of publication of application : **02.11.1999**

(51)Int.Cl. **C08F279/00**

(21)Application number : **10-122695** (71)Applicant : **TECHNO POLYMER KK**

(22)Date of filing : **17.04.1998** (72)Inventor : **YAMAWAKI KAZUTADA
NAKAGAWA TOMOJI
MOTAI MASAOKI**

(54) RUBBER-MODIFIED THERMOPLASTIC RESIN

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a rubber-modified thermoplastic resin with excellent impact resistance, weatherability, appearance after molded, chemical resistance, scratch resistance and slidability.

SOLUTION: This rubber-modified thermoplastic resin with a graft percentage of 10-100% and the intrinsic viscosity $[\eta]$ of methyl ethyl ketone solubles of 0.2-0.8 dL/g, is obtained by graft polymerization of at least one monomer component selected from the group consisting of aromatic vinyl compounds, vinyl cyanide compounds and other vinyl monomers copolymerizable therewith in the presence of (A) a rubbery polymer $\geq 70^{\circ}\text{C}$ in melting point T_m composed of ethylene, a 3-20C α -olefin and a non-conjugated diene in the weight ratio of (5-95):(95-5):(0-30) and (B) a 2nd rubbery polymer $< 70^{\circ}\text{C}$ in melting point T_m or with no T_m in the weight ratio A/B of (10-90):(90-10).

LEGAL STATUS

[Date of request for examination] **13.01.2005**

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]